

## NORMA INTERNACIONAL DE BLINDADORES NIJ

**Table 1. Test Summary**

Armor Type	Test Variables			Performance Requirements		
	Test Ammunition	Nominal Bullet Mass	Suggested Barrel Length	Required Bullet Velocity	Required Fair Hits per armor specimen	Permitted Penetrations
I	22 LRHV Lead	2.6 g 40 gr	15- 16.5 cm 6 - 6.5 in	320 ± 12 m/s 1050 ± 40 ft/s	5	0
	38 Special RN Lead	10.2 g 158 gr	15- 16.5 cm 6 - 6.5 in	259 ± 15 m/s 850 ± 50 ft/s	5	0
II-A	357 Magnum JSP	102 g 158 gr	10 - 12 cm 4 - 4.75 in	381 ± 15 m/s 1250 ± 50 ft/s	5	0
	9 mm FMJ	2.6 g 40 gr	15- 16.5 cm 6 - 6.5 in	332 ± 12 m/s 1090 ± 40 ft/s	5	0
II	357 Magnum JSP	10.2 g 158 gr	15 - 16.5 cm 6 - 6.5 in	425 ± 15 m/s 1395 ± 50 ft/s	5	0
	9 mm FMJ	8.0 g 124 gr	10 - 12 cm 4 - 4.75 in	358 ± 12 m/s 1175 ± 40 ft/s	5	0
III-A	44 Magnum Lead SWC Gas Checked	15.55 g 240 gr	14 - 16cm 5.5 - 6.25in	426 ± 15 m/s 1400 ± 50 ft/s	5	0
	9 mm FMJ	8.0 g 124 gr	24 - 26 cm 9.5 - 10.25 in	426 ± 15 m/s 1400 ± 50 ft/s	5	0
III	7.62 mm (308 Winchester) FMJ	9.7 g 150 gr	56 cm 22 in	838 ± 15 m/s 2750 ± 50 ft/s	5	0
IV	30-06 AP	10.8 g 166 gr	56 cm 22 in	868 ± 15 m/s 2850 ± 50 ft/s	5	0
Special Requirement	*	*	*	*	*	*

Fuente: <http://www.ballisticedge.com.au>